

(11)Publication number:

57-027130

(43) Date of publication of application: 13.02.1982

(51)Int.Cl.

B01J 20/20 B01D 39/20 B01J 20/28 C01B 31/08 CO4B 35/52

(21)Application number : 55-103814

(71)Applicant : KOBE STEEL LTD

(22) Date of filing:

28.07.1980

(72)Inventor: KUMAZAWA KOJI

SAURA EIJI

NIKAIDO MITSUNOBU KOBAYASHI KOICHI **SUGINO MORIHIKO**

(54) PRODUCTION OF HONEYCOMB LIKE FORMED BODY OF ACTIVATED CARBON (57) Abstract:

PURPOSE: To produce a honeycomb formed body of an activated carbon precisely by kneading cut fibers of a thermosetting resin having a ratio of the fiber length to the diameter which is equal to or below a specific value with a thermosetting binder and forming this mixture into a honeycomb like shape, then, drying it, and ativating it by heating after carbonized in a nonoxidizing atmosphere.

CONSTITUTION: Into thermosetting cut fibers having ≤80 ratio of the fiber length to the diameter, a thermosetting binder is added and kneaded, and this mixture is extended into a honeycomb shape. For the thermosetting resin, a resin of a phenol type, or a furan type, or a xylene-formaldehyde type or the like is used, and for the thermosetting binder, an adhesive agent of a phenol resin, or a melamine resin, or a formaldehyde resin or the like is used. After this honeycomb formed body is dried, this body is carbonized in a nonoxidizing atmosphere at about 500W1,100°C, then activated in an oxidizing atmosphere by the conventional method.

LEGAL STATUS

[Date of request for examination]

[Date of sending the examiner's decision of

Seite 2 von 2

rejection]

[Kind of final disposal of application other than the examiner's decision of rejection or application converted registration]

[Date of final disposal for application]

[Patent number]

[Date of registration]

[Number of appeal against examiner's decision of rejection]

[Date of requesting appeal against examiner's decision of rejection]

[Date of extinction of right]

Copyright (C); 1998,2003 Japan Patent Office